

PRODUCT INFORMATION
OKULEN® 2000 - MD - FN7790

OKULEN® 2000 - MD - FN7790 is a "Metal detectable" UHMW-PE polymer compound with a molecular weight of 7 - 9 mio. g/mol.. The material has a good abrasion resistance, less wear, a low coefficient of friction and a high impact strength.

Properties:

- good sliding properties
- good abrasion resistance
- less wear
- metal detectable
- EU1935/2004 - conform
- EU10/2011 - conform
- FDA - conform

Colour:

anthracite-black FN7790 / similar RAL7021

Range of applications:

- Food industry
- Conveyor industry

PRODUCT INFORMATION

OKULEN® 2000 - MD - FN7790

Characteristics and standard values

Properties	Method	OKULEN® 2000 - MD - FN7790	
		SI	US
Physical properties			
Molecular-weight	k.a.	7.0 - 9.0 Mio. g/mol.	7.0 - 9.0 Mio. g/mol.
Density	DINENISO 1183-1 (09/2019) ASTM D792	> 0.945 g/cm³	> 58.994 lb/ft³
Notched impact strength	DINENISO 21304-2 (04/2021)	>110 kJ/m²	>52.305 ft-lb/in²
Abrasion-Index (Sand-Slurry)	DINENISO 15527 (05/2022)	85	85
Tensile strength at yield (1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 17 N/mm²	> 2465 psi
	---	---	---
Elongation (Break / 1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 200 %	> 200 %
Tensile-E-modulus (1B - 1mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 650 N/mm²	> 94250 psi
	---	---	---
Static Friction	ASTM D 1894 (2014)	~ 0.2	~ 0.2
Dynamic Friction	ASTM D 1894 (2014)	~ 0.18	~ 0.18
Shore-D-Hardness, 3 sec. value 6 mm plate	DINENISO 868 (10/2003)	65 - 67 D	65 - 67 D
Ball indentation hardness	DINENISO 2039	--- N/mm²	--- psi
Water absorption	DINENISO 62 (05/2008)	< 0.01 %	< 0.01 %
Thermal properties			
Melting Point (DSC)	DINENISO 11357-1 (03/2010)	135 - 137 °C	275 - 278.6 °F
Thermal Conductivity	Wire method	~ 0.41 W/m*K	~ 2.84253 (BTU-in)/hr-ft²-°F
Max. operation temperature	Literature	~ 80 °C	~ 176 °F
Coefficient of thermal expansion (23 - 80°C)	ISO 11359	~ 0.00015 - 0.00020 mm/mm °C	~ 0.000083 - 0.000111 in/in °F
Electrical properties			
Volume resistivity	DINEN 62631-3-1 (01/2017)	< 1.0E14 Ohm*cm	< 1.0E14 Ohm*cm
Surface resistivity	DINEN 62631-3-2 (10/2016)	< 1.0E13 Ohm	< 1.0E13 Ohm
ATEX-Directive - TÜV approved!	ATEX-Directive	---	---
ESD-D	---	--- Ohm	--- Ohm
Burning properties			
Fire resistance (Self-classification)	DIN 4102	B2 Klasse	B2 Class
Fire resistance (Self-classification)	UL94	HB Klasse	HB Class
Physiological properties			
Food compliant		EU/FDA	EU/FDA

Ottensteiner Kunststoff GmbH & Co. KG

Im Garbrock 39, 48683 Ahaus-Ottenstein Germany

Phone: +49 (0) 2561-9824-0

Internet: www.okulen.com

e-mail: info@okulen.com