

PRODUCT INFORMATION
OKULEN® 500 Reg.-black-multi-FN9005

OKULEN® 500-Reg. (PE-HMW)

High molecular weight low pressure polyethylene with regenerated materials.

Colour: black multi-coloured OK-FN: 9005

Characteristics and standard values

Properties	Method	OKULEN® 500 Reg.-black-multi-FN9005	
		SI	US
Physical properties			
Molecular-weight	k.a.	0,5 Mio. g/mol.	0.5 Mio. g/mol.
Density	DINENISO 1183-1 (04/2013) ASTM D792	0,960 g/cm ³	59.931 lb/ft ³
Notched impact strength	DINENISO 11542-2 (01/2010)	15 kJ/m ²	7.1325 ft-lb/in ²
Abrasion-Index (Sand-Slurry)	DINENISO 15527 (05/2013)	>250 - 450	>250 - 450
Tensile strength at yield (1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 20 N/mm ²	> 2900 psi
	---	---	---
Elongation (Break / 1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 150 %	> 150 %
Tensile-E-modulus (1B - 1mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	900 N/mm ²	130500 psi
	---	---	---
Static Friction	ASTM D 1894 (2011)	~ 0,16 - 0,22	~ 0.16 - 0.22
Dynamic Friction	ASTM D 1894 (2011)	~ 0,10 - 0,17	~ 0.10 - 0.17
Shore-D-Hardness, 3 sec. value 6 mm plate	DINENISO 868 (10/2003)	65 - 67 D	65 - 67 D
Ball indentation hardness	DINENISO 2039	48 N/mm ²	6960 psi
Water absorption	DINENISO 62 (05/2008)	< 0,01 %	< 0.01 %
Thermal properties			
Melting Point (DSC)	DINENISO 11357-1 (03/2010)	133 - 137 °C	271.4 - 278.6 °F
Thermal Conductivity	Wire method	0,41 W/m*K	2.84253 (BTU-in)/hr-ft ² -°F
Max. operation temperature	Literature	80 °C	176 °F
Coefficient of thermal expansion (23 - 80°C)	ISO 11359	0,00015 - 0,00020 mm/mm °C	0.000083 - 0.000111 in/in °F
Electrical properties			
Volume resistivity	DINEN 62631-3-1 (01/2017)	< 1.0E14 Ohm*cm	< 1.0E14 Ohm*cm
Surface resistivity	DINEN 62631-3-2 (10/2016)	< 1.0E13 Ohm	< 1.0E13 Ohm
ATEX-Directive - TÜV approved!	ATEX-Directive	---	---
ESD-D	---	--- Ohm	--- Ohm
Burning properties			
Fire resistance (Self-classification)	DIN 4102	B2 Klasse	B2 Class
Fire resistance (Self-classification)	UL94	HB Klasse	HB Class
Physiological properties			
Food compliant		---	---

The above data are based on the present knowledge and are given without guarantee. Existing laws and conditions are to be respected by the user of our products. The decision about the suitability of a material for a certain application must be made by the user. We reserve the right to alter the indicated data. The indicated values are for a 15 mm thick sheet.

Ottensteiner Kunststoff GmbH & Co. KG

Im Garbrock 39, 48683 Ahaus-Ottenstein
 Germany

Phone: +49 (0) 2561-9824-0

Internet: www.okulen.com

e-mail: info@okulen.com