

**PRODUCT INFORMATION**  
**OKULEN<sup>®</sup> PP B - Pebble grey - FN7032**

OKULEN<sup>®</sup> PP B is a pebble grey basic stabilisation polypropylene blockcopolymer with high melt viscosity and good low-temperature impact strength.

Properties:

- good chemical resistance
- high heat deflection temperature
- easy to work and weld

Colour:

Pebble grey FN7032 / similar RAL7032

Range ofapplications:

- Punching pads

**Ottensteiner Kunststoff GmbH & Co. KG**

Im Garbrock 39, 48683 Ahaus-Ottenstein&lt;br&gt;Germany

Phone: +49 (0) 2561-9824-0

Internet: [www.okulen.com](http://www.okulen.com)e-mail: [info@okulen.com](mailto:info@okulen.com)

**PRODUCT INFORMATION**  
**OKULEN® PP B - Pebble grey - FN7032**

## Characteristics and standard values

Properties	Method	OKULEN® PP B - Pebble grey - FN7032	
		SI	US
<b>Physical properties</b>			
Molecular-weight	k.a.	--- Mio. g/mol.	--- Mio. g/mol.
Density	DINENISO 1183-1 (09/2019) ASTM D792	> 0.901 g/cm <sup>3</sup>	> 56.247 lb/ft <sup>3</sup>
Notched impact strength	DINENISO 21304-2 (04/2021)	> 20 kJ/m <sup>2</sup>	> 9.51 ft-lb/in <sup>2</sup>
Abrasion-Index (Sand-Slurry)	DINENISO 15527 (05/2022)	---	---
Tensile strength at yield (1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	> 25 N/mm <sup>2</sup>	> 3625 psi
	---	---	---
Elongation (Break / 1B - 50mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	--- %	--- %
Tensile-E-modulus (1B - 1mm/Min.)	DINENISO 527-2 (06/2012) ASTM D 638 (2010)	1200 N/mm <sup>2</sup>	174000 psi
	---	---	---
Static Friction	ASTM D 1894 (2014)	---	---
Dynamic Friction	ASTM D 1894 (2014)	---	---
Shore-D-Hardness, 3 sec. value 6 mm plate	DINENISO 868 (10/2003)	72 - 74 D	72 - 74 D
Ball indentation hardness	DINENISO 2039	--- N/mm <sup>2</sup>	--- psi
Water absorption	DINENISO 62 (05/2008)	< 0.01 %	< 0.01 %
<b>Thermal properties</b>			
Melting Point (DSC)	DINENISO 11357-1 (03/2010)	158 - 165 °C	316.4 - 329 °F
Thermal Conductivity	Wire method	~ 0.22 W/m*K	~ 1.52526 (BTU-in)/hr-ft <sup>2</sup> -°F
Max. operation temperature	Literature	100 °C	212 °F
Coefficient of thermal expansion (23 - 80°C)	ISO 11359	~0.00015 - 0.00020 mm/mm °C	~0.000083 - 0.000111 in/in °F
<b>Electrical properties</b>			
Volume resistivity	DINEN 62631-3-1 (01/2017)	> 1.0E15 Ohm*cm	> 1.0E15 Ohm*cm
Surface resistivity	DINEN 62631-3-2 (10/2016)	> 1.0E15 Ohm	> 1.0E15 Ohm
ATEX-Directive - TÜV approved!	ATEX-Directive	---	---
ESD-D	---	--- Ohm	--- Ohm
<b>Burning properties</b>			
Fire resistance (Self-classification)	DIN 4102	B2 Klasse	B2 Class
Fire resistance (Self-classification)	UL94	HB Klasse	HB Class
<b>Physiological properties</b>			
Food compliant		EU/FDA	EU/FDA

**Ottensteiner Kunststoff GmbH & Co. KG**

Im Garbrock 39, 48683 Ahaus-Ottenstein Germany

Phone: +49 (0) 2561-9824-0

Internet: [www.okulen.com](http://www.okulen.com)

e-mail: [info@okulen.com](mailto:info@okulen.com)